



# 100% MATERIAL DECLARATION FORM

Pressure Sensitive Label Material					
Sample Size (W x L x thickness) mm					(100 x 100 x 0.1346)mm
Package Total Mass (g)					1.86032
Comments	POLYONICS PART NUMBER ---- XF 594				
Component	Substance	CAS Number	Amount of Substance (mg)	Percentage %	ppm
<b>Printable Coating</b>					
Pigment	Titanium Dioxide	13463-67-7	175.6mg	9.4392	94392
Catalyst	Proprietary	-----	0.7248mg	0.0389	389
Flow Additive	Proprietary	-----	3.623mg	0.1947	1947
Polymer Binder	Proprietary Resin	-----	70.47mg	3.7880	37880
Polymer Binder	Proprietary Resin	-----	4.506mg	0.2422	2422
<b>Base Film</b>					
Polyimide film	Polyimide Polymer	25038-81-7	340mg	18.2763	182763
<b>Pressure Sensitive Adhesive</b>					
Adhesive	Proprietary Silicone Polymer	31074-60-9	546mg	29.3497	293497
<b>Release Liner</b>					
Fluorine Substituted Silicone Coating	Proprietary	-----	6.5mg	0.3494	3494
Base Film	Polyester Film	25038-59-9	712.9mg	38.3212	383212
<b>Sum</b>			<b>1.86032</b>	<b>100.00</b>	<b>1000000</b>