

**Description:** Polyonics XF-801 is high temperature aluminum label material has a permanent pressure sensitive, high temperature acrylic adhesive and a **high opacity, white topcoat** specifically designed for thermal transfer printing. Do not touch topcoat or ribbon print when hot as smearing may occur, once cooled topcoat and ribbon are bonded and smear resistant.

**Use:** Polyonics XF-801 aluminum label material is designed for barcode or alphanumeric identification of hot items. These labels withstand the hot environments of heat treating and baking in the metal and ceramic processes. Ideal for environments where long term heat exposure prohibits the use of synthetics such as polyester, PEN and polyimide. Name and Rating plates, track and trace labeling and many other applications.

**Printer Technology:** The choice of **thermal transfer** printer influences the print quality for the overall aluminum tag performance. Our materials can be used with most high performance industrial thermal transfer printers. **Testing for specific printer and ribbon is mandatory.**

Properties	Test Method	Average Results	
		USA Units	SI Units
<b>Thickness</b>	<b>ASTM D1000</b>		
<b>-Substrate</b>		0.0024 inch	0.061 mm
<b>-Adhesive</b>		0.0010 inch	0.025 mm
<b>-Total</b>		0.0034 inch	0.086 mm
<b>Thermal Characteristics</b>	Operating Temp. -148 °F to +842°F (-100°C to 450°C) Application Temp. 68°F to +104°F (20°C to 40°C)		
<b>Shelf Life*</b>	<b>1 year below 80°F (27°C) and 60% R.H.</b>		
<b>Ribbon recommendations</b>	Ricoh B110A		

**Note.** All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by POLYONICS customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact POLYONICS for further information.



**References:**

ASTM: American Society for Testing and Materials (U.S.A.)

SI: International Systems of Units. All SI units are mathematically derived from U.S. conventional units.

\* **Shelf Life:** XF-801 aluminum label material can be stored for at least **1 Year** in an environment below 80° F and 60% RH. We are confident that our product will perform well beyond this time frame; however, it remains the responsibility of the user to assess the risk of using such product. We encourage customers to develop functional testing protocols that will qualify a product's fitness for use, in their actual applications.

**Surface conditions:** Slight surface imperfections such as micro-cracks, pick-up (sparkles or bumps) and die lines are often caused by local variations in the microstructure of the foil due to size and



POLYONICS METALGARD®

**XF-801**

**Thermal Transfer Printable Aluminum**

**White**

2

distribution of inter-metallic particles, grain size and grain orientation/texture. Such imperfections are common and beyond our control. This material is not recommended for high density small print labels.

#### **WARRANTY-LIMITATION**

Polyonics' products are sold with the understanding that the buyer will test them in actual use and determine for him/herself their functionality for the intended uses. Polyonics warrants to the buyer that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the products shown to Polyonics' satisfaction to have been defective, provided that the Buyer has complied with the handling, storage and shelf life requirements as specified by Polyonics in applicable materials specifications.

The above warranties extend solely to Buyer and all warranty claims must be made by Buyer. Rework or Replacement shall neither extend nor decrease the original warranty period. The term of all warranty periods shall not exceed thirty (30) days from the date of the original shipment.

**THE ABOVE WARRANTIES ARE EXCLUSIVE OF AND IN LIEU OF ALL OTHER WARRANTIES, WRITTEN OR ORAL, EXPRESS OR IMPLIED, STATUTORY OR OTHERWISE. NO IMPLIED STATUTORY WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE SHALL APPLY. POLYONICS SHALL NOT BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OR INABILITY TO USE THE PRODUCT, OR FROM DELAY IN THE REPLACEMENT OR REPAIR OF PRODUCTS UNDER THE ABOVE WARRANTY.**